

Customer No.: 31561
Application No.: 10710,621
Docket No.: 11576-US-PA

Amendment

IN THE CLAIMS

Claim 1. (original) A bumping process, comprising:

providing a wafer having a plurality of bonding pads and a passivation layer having a plurality openings thereon, wherein the bonding pads are exposed out of the openings of the passivation layer;

forming an under-bump-metallurgy layer on the wafer and covering the bonding pads;

forming a first photoresist layer over the wafer to cover the bonding pads and the passivation layer;

forming a second photoresist layer on the first photoresist layer, wherein the first photoresist layer has exposure/development characteristics different from that of the second photoresist layer;

performing a single exposure process to the first and second photoresist layers to form a plurality of first openings in the first photoresist layer and a plurality of second openings in the second photoresist layer simultaneously, wherein a plurality of stair-shaped openings are formed from the first openings and the second openings and expose the under-bump-metallurgy layer;

filling a solder material into the stair-shaped openings to form a plurality of solder posts; and

Customer No.: 31561
Application No.: 10710,621
Docket No.: 11576-US-PA

removing the first photoresist layer and the second photoresist layer.

Claim 2. (original) The bumping process of claim 1, further comprising reflowing the solder posts to form a plurality of bumps over the under-bump-metallurgy layer, after removing the first and second photoresist layers.

Claim 3. (original) The bumping process of claim 1, wherein the first openings are smaller than the second openings.

Claim 4. (original) The bumping process of claim 1, wherein the first photoresist layer has a photosensitivity lower than that of the second photoresist layer.

Claim 5. (original) The bumping process of claim 1, wherein the first photoresist layer comprises a spin-coated photoresist or a dry film.

Claim 6. (original) The bumping process of claim 1, wherein the second photoresist layer is a liquid state spin-coated photoresist or a dry film.

Claim 7. (original) The bumping process of claim 1, wherein the method of filling the solder material comprises electroplating or stencil printing.

Claim 8. (currently amended) A bumping process, comprising:

providing a wafer having a plurality of bonding pads and a passivation layer having a plurality of openings thereon, wherein the bonding pads are exposed out of the openings of the passivation layer;

forming an under-bump-metallurgy layer on the wafer to cover the bonding pads;

forming a plurality of photoresist layers on the wafer to cover the bonding pads

Customer No.: 31561
Application No.: 10710,621
Docket No.: 11576-US-PA

and the passivation layers, wherein the photoresist layers have different photosensitivities;

forming a plurality of stair-like openings located above the bonding pads in the photoresist layers by an single exposure process, wherein the under-bump-metallurgy layer is exposed out of the stair-shaped openings;

filling a solder material into the stair-shaped openings to form a plurality of solder posts; and

removing the photoresist layers.

Claim 9. (currently amended) The bumping process of claim 8, further comprising the step of reflowing the solder posts to form a plurality of bumps on the under-bump-metallurgy ~~metal~~ layer, after removing the photoresist layers.

Claim 10. (original) The bumping process of claim 8, wherein a size of the stair-like openings in the lower photoresist layer that is closer to the bonding pads is smaller than that of the stair-shaped openings in the higher photoresist layer that is farther away from the bonding pads.

Claim 11. (original) The bumping process of claim 8, wherein the photoresist layer that is farthest away from the bonding pads has the highest photosensitivity, while the photoresist layer that is closest to the bonding pads has the lowest photosensitivity.

Claim 12. (original) The bumping process of claim 8, wherein the photoresist layers comprise a spin-coated photoresist.

Customer No.: 31561
Application No.: 10710,621
Docket No.: 11576-US-PA

Claim 13. (original) The bumping process of claim 8, wherein the photoresist layers comprise a dry film.

Claim 14. (original) The bumping process of claim 8, wherein the method of filling the solder material comprises electroplating or stencil printing.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.